

WASTE STREAM	2C933	MAETP ILW Resin
---------------------	--------------	------------------------

SITE Chapelcross
SITE OWNER Nuclear Decommissioning Authority
WASTE CUSTODIAN Magnox Limited
WASTE TYPE ILW

WASTE VOLUMES

		Reported
Stocks:	At 1.4.2019.....	0 m ³
Future arisings -	1.4.2020 - 31.3.2021.....	<0.5 m ³
Total future arisings:		0.5 m ³
Total waste volume:		0.5 m ³

Comment on volumes: 150 litres of resin = 0.45m3.

Uncertainty factors on volumes:
 Stock (upper): x Arisings (upper) x 1.1
 Stock (lower): x Arisings (lower) x 0.5

WASTE SOURCE Operation of the MAETP to drain down Pond 2 will result in this inorganic resin.

PHYSICAL CHARACTERISTICS

General description: Titanosilicate is an inorganic IEX similar in structure and composition to those currently used at MX (e.g. aluminosilicate AW500).

Physical components (%vol): Titanosilicate inorganic Ion Exchange resin (100%).

Sealed sources: -

Bulk density (t/m³): 1

Comment on density: Unknown. 1 t/m3 used as interim value.

CHEMICAL COMPOSITION

General description and components (%wt): Kurion TS-G resin. Titanosilicate inorganic Ion Exchange resin (100%).

Chemical state: Neutral

Chemical form of radionuclides: -

Metals and alloys (%wt): -

- Stainless steel.....
- Other ferrous metals.....
- Iron.....
- Aluminium.....
- Beryllium.....
- Cobalt.....
- Copper.....
- Lead.....
- Magnox/Magnesium.....
- Nickel.....
- Titanium.....
- Uranium.....
- Zinc.....
- Zircaloy/Zirconium.....
- Other metals.....

Organics (%wt): -

WASTE STREAM	2C933	MAETP ILW Resin
---------------------	--------------	------------------------

Total cellulose..... 0
 Paper, cotton.....
 Wood.....
 Halogenated plastics
 Total non-halogenated plastics..... 0
 Condensation polymers.....
 Others.....
 Organic ion exchange materials....
 Total rubber..... 0
 Halogenated rubber
 Non-halogenated rubber.....
 Hydrocarbons.....
 Oil or grease
 Fuel.....
 Asphalt/Tarmac (cont.coal tar)...
 Asphalt/Tarmac (no coal tar)....
 Bitumen.....
 Others.....
 Other organics.....

Other materials (%wt):

-
 Inorganic ion exchange materials. 100.0
 Inorganic sludges and flocs.....
 Soil.....
 Brick/Stone/Rubble.....
 Cementitious material.....
 Sand.....
 Glass/Ceramics.....
 Graphite.....
 Desiccants/Catalysts.....
 Asbestos.....
 Non/low friable.....
 Moderately friable.....
 Highly friable.....
 Free aqueous liquids.....
 Free non-aqueous liquids.....
 Powder/Ash.....

Titanosilicate inorganic Ion Exchange resin

Inorganic anions (%wt):

-

- Fluoride.....
- Chloride.....
- Iodide.....
- Cyanide.....
- Carbonate.....
- Nitrate.....
- Nitrite.....
- Phosphate.....
- Sulphate.....
- Sulphide.....

Materials of interest for waste acceptance criteria:

-
- Combustible metals.....
- Low flash point liquids.....
- Explosive materials.....
- Phosphorus.....
- Hydrides.....
- Biological etc. materials.....
- Biodegradable materials.....
 - Putrescible wastes.....
 - Non-putrescible wastes.....
- Corrosive materials.....
- Pyrophoric materials.....
- Generating toxic gases.....
- Reacting with water.....
- Active particles.....
- Soluble solids as bulk chemical compounds.....

Hazardous substances / non hazardous pollutants:

-
- Acrylamide.....
- Benzene.....
- Chlorinated solvents.....
- Formaldehyde.....
- Organometallics.....
- Phenol.....
- Styrene.....
- Tri-butyl phosphate.....
- Other organophosphates.....
- Vinyl chloride.....
- Arsenic.....
- Barium.....
- Boron.....

WASTE STREAM	2C933	MAETP ILW Resin
---------------------	--------------	------------------------

- Cadmium.....
- Caesium.....
- Selenium.....
- Chromium.....
- Molybdenum.....
- Thallium.....
- Tin.....
- Vanadium.....
- Mercury compounds.....
- Others.....
- Electronic Electrical Equipment (EEE)
 - EEE Type 1.....
 - EEE Type 2.....
 - EEE Type 3.....
 - EEE Type 4.....
 - EEE Type 5.....

Complexing agents (%wt):

- EDTA.....
- DPTA.....
- NTA.....
- Polycarboxylic acids.....
- Other organic complexants.....
- Total complexing agents.....

PACKAGING AND CONDITIONING

Conditioning method: CX plan to utilise the titanosilicate IEX resin cartridges in their MAETP to treat 1800m³ filtered pond water from CX pond 2, packaging the resulting IEX material in a MOSAIK T-ISAR or II-15 EI DCIC. Up to 450L IEX material is expected to be required, equivalent to one MOSAIK DCIC waste package. Packaged wastes will comprise the IEX resin only, in absence of the metal cartridge casing and solids filtered prior to ion exchange. Packaged IEX material will be conditioned on AVDS (criteria for the cessation of vacuum drying to be confirmed).

- Plant Name: -
- Location: -
- Plant startup date: -
- Total capacity (m³/y incoming waste): -
- Target start date for packaging this stream: -
- Throughput for this stream (m³/y incoming waste): -
- Other information: -

Likely container type:	Container	Waste packaged (%vol)	Waste loading (m ³)	Payload (m ³)	Number of packages
	500 l RS drum (0mm Pb)	100.0	0.45	0.49	1

WASTE STREAM	2C933	MAETP ILW Resin
---------------------	--------------	------------------------

Likely container type comment: -

Range in container waste volume: -

Other information on containers: -

Likely conditioning matrix: Other information: -

Conditioned density (t/m³): -

Conditioned density comment: -

Other information on conditioning: -

Opportunities for alternative disposal routing:

Treatment	Stream volume (%)	Comment
-	-	-

RADIOACTIVITY

Source: -

Uncertainty: From application of the current CX pond water safety case limits, the wastes will contain no more than 27 GBq Cs-137 and 145 GBq Sr-90 at 2040.

Definition of total alpha and total beta/gamma: Where totals are shown on the table of radionuclide activities they are the sums of the listed alpha or beta/gamma emitting radionuclides plus 'other alpha' or 'other beta/gamma'.

Measurement of radioactivities: -

Other information: -

WASTE STREAM 2C933 MAETP ILW Resin

Nuclide	Mean radioactivity, TBq/m ³				Nuclide	Mean radioactivity, TBq/m ³			
	Waste at 1.4.2019	Bands and Code	Future arisings	Bands and Code		Waste at 1.4.2019	Bands and Code	Future arisings	Bands and Code
H 3					Gd 153				
Be 10					Ho 163				
C 14					Ho 166m				
Na 22					Tm 170				
Al 26					Tm 171				
Cl 36					Lu 174				
Ar 39					Lu 176				
Ar 42					Hf 178n				
K 40					Hf 182				
Ca 41					Pt 193				
Mn 53					Tl 204				
Mn 54					Pb 205				
Fe 55					Pb 210				
Co 60					Bi 208				
Ni 59					Bi 210m				
Ni 63					Po 210				
Zn 65					Ra 223				
Se 79					Ra 225				
Kr 81					Ra 226				
Kr 85					Ra 228				
Rb 87					Ac 227				
Sr 90					Th 227				
Zr 93					Th 228				
Nb 91					Th 229				
Nb 92					Th 230				
Nb 93m					Th 232				
Nb 94					Th 234				
Mo 93					Pa 231				
Tc 97					Pa 233				
Tc 99					U 232				
Ru 106					U 233				
Pd 107					U 234				
Ag 108m					U 235				
Ag 110m					U 236				
Cd 109					U 238				
Cd 113m					Np 237				
Sn 119m					Pu 236				
Sn 121m					Pu 238				
Sn 123					Pu 239				
Sn 126					Pu 240				
Sb 125					Pu 241				
Sb 126					Pu 242				
Te 125m					Am 241				
Te 127m					Am 242m				
I 129					Am 243				
Cs 134					Cm 242				
Cs 135					Cm 243				
Cs 137					Cm 244				
Ba 133					Cm 245				
La 137					Cm 246				
La 138					Cm 248				
Ce 144					Cf 249				
Pm 145					Cf 250				
Pm 147					Cf 251				
Sm 147					Cf 252				
Sm 151					Other a				
Eu 152					Other b/g				
Eu 154					Total a	0			NE
Eu 155					Total b/g	0			NE

Bands (Upper and Lower)

- A a factor of 1.5
- B a factor of 3
- C a factor of 10
- D a factor of 100
- E a factor of 1000

Note: Bands quantify uncertainty in mean radioactivity.

Code

- 1 Measured activity
- 2 Derived activity (best estimate)
- 3 Derived activity (upper limit)
- 4 Not present
- 5 Present but not significant
- 6 Likely to be present but not assessed
- 7 Present in significant quantities but not determined
- 8 Not expected to be present in significant quantity