

<b>WASTE STREAM</b>	<b>9A51</b>	<b>FED Stainless Steel</b>
---------------------	-------------	----------------------------

**SITE** Berkeley

**SITE OWNER** Nuclear Decommissioning Authority

**WASTE CUSTODIAN** Magnox Limited

**WASTE TYPE** ILW

**WASTE VOLUMES**

		Reported
Stocks:	At 1.4.2019.....	0.1 m <sup>3</sup>
Total future arisings:		0 m <sup>3</sup>
Total waste volume:		0.1 m <sup>3</sup>

Comment on volumes: Station operation ceased in March 1989. This waste stream was accumulated between May 1991 and December 1993. The stainless steel was used for flux flattening and was replaced by zirconium on later elements as fuel irradiation had increased and flux flattening by the stainless steel was not required. The volume quoted is the estimated bulk volume of the waste if separated from other wastes with which it is mixed.

Uncertainty factors on volumes:	Stock (upper):	x 1.1	Arisings (upper)	x
	Stock (lower):	x 0.9	Arisings (lower)	x

**WASTE SOURCE** The source of the waste is the removal of graphite struts and associated zirconium and stainless steel bridge pieces from fuel elements prior to dispatch of the elements to Sellafield.

**PHYSICAL CHARACTERISTICS**

General description: The waste comprises predominantly stainless steel bridge pieces. The bridge pieces may still be connected to the graphite struts (see waste stream 9A35). Approximately 38% of fuel elements used stainless steel top support bridges, (with the rest being zirconium). There will also be a small quantity of nimonic springs, which may be attached to thermocouple wires. A stainless steel top support bridge is 127mm in length and weighs approximately 26g and a Nimonic spring weighs approximately 5g. The thermocouple wires are approximately 380mm in length. It is unlikely that there will be any large items which will require special handling. The waste is loose in the vaults.

Physical components (%wt): Stainless steel bridge pieces (>98.5% wt), Nimonic springs (~0.75% wt) and thermocouples wires (0.75% wt).

Sealed sources: -

Bulk density (t/m<sup>3</sup>): 2.6

Comment on density: The average bulk density of 2.6 t/m<sup>3</sup> assumes a packing factor to give an overall volume of about three times the displacement volume of the waste.

**CHEMICAL COMPOSITION**

General description and components (%wt): Stainless steel will account for more than 98.5% of the waste, with 0.75% Nimonic and 0.25%, alumina, magnesia and other minor constituents. The stainless steel may be contaminated with fission product, actinides and graphite.

Chemical state: Neutral

Chemical form of radionuclides: H-3: Tritium will probably be present as surface contamination, possibly as water or perhaps as other inorganic or organic compounds.  
 C-14: Carbon 14 may be present as carbon incorporated in the stainless steel and is likely to be in the form of graphite contamination.  
 Cl-36: Chlorine 36 will probably be present in surface contamination.  
 Se-79: The selenium content is insignificant.  
 Tc-99: The technetium content is insignificant.  
 Ra: Radium isotope content is insignificant.  
 Th: The thorium isotope content is insignificant.  
 U: Chemical form of uranium isotopes has not been determined but may be uranium oxides.  
 Np: The neptunium content is insignificant.  
 Pu: Chemical form of plutonium isotopes has not been determined but may be plutonium oxides.

Metals and alloys (%wt): The items will typically be 127 mm x 25 mm x 17 mm.

**WASTE STREAM****9A51****FED Stainless Steel**

Stainless steel.....	~99.0	
Other ferrous metals.....	0	
Iron.....		
Aluminium.....	0	
Beryllium.....	0	
Cobalt.....		
Copper.....	0	
Lead.....	0	
Magnox/Magnesium.....	0	
Nickel.....	~0.75	Nimonic.
Titanium.....		
Uranium.....		
Zinc.....	0	
Zircaloy/Zirconium.....	0	
Other metals.....	0	No "other" metals have been identified.

**Organics (%wt):**

The stainless steel may be contaminated with trace quantities of organic material.

Total cellulose.....	0
Paper, cotton.....	0
Wood.....	0
Halogenated plastics .....	0
Total non-halogenated plastics.....	0
Condensation polymers.....	0
Others.....	0
Organic ion exchange materials....	0
Total rubber.....	0
Halogenated rubber .....	0
Non-halogenated rubber.....	0
Hydrocarbons.....	
Oil or grease .....	
Fuel.....	
Asphalt/Tarmac (cont.coal tar)...	
Asphalt/Tarmac (no coal tar)....	
Bitumen.....	
Others.....	
Other organics.....	TR

**Other materials (%wt):**

Graphite contamination.	
Inorganic ion exchange materials.	0
Inorganic sludges and flocs.....	0
Soil.....	0
Brick/Stone/Rubble.....	0
Cementitious material.....	0
Sand.....	

<b>WASTE STREAM</b>	<b>9A51</b>	<b>FED Stainless Steel</b>
---------------------	-------------	----------------------------

Glass/Ceramics..... 0  
 Graphite..... TR  
 Desiccants/Catalysts.....  
 Asbestos..... 0  
     Non/low friable.....  
     Moderately friable.....  
     Highly friable.....  
 Free aqueous liquids..... TR  
 Free non-aqueous liquids..... 0  
 Powder/Ash..... P

Inorganic anions (%wt): None of the inorganic anions listed in the table is expected to be present at greater than trace concentration.

Fluoride..... TR  
 Chloride..... TR  
 Iodide..... 0  
 Cyanide..... 0  
 Carbonate..... TR  
 Nitrate..... TR  
 Nitrite..... TR  
 Phosphate..... TR  
 Sulphate..... TR  
 Sulphide..... 0

Materials of interest for waste acceptance criteria: There are no identified materials likely to represent a fire or other non-radiological hazard.

Combustible metals..... 0  
 Low flash point liquids..... 0  
 Explosive materials..... 0  
 Phosphorus..... 0  
 Hydrides..... 0  
 Biological etc. materials..... 0  
 Biodegradable materials.....  
     Putrescible wastes..... 0  
     Non-putrescible wastes.....  
 Corrosive materials..... 0  
 Pyrophoric materials..... 0  
 Generating toxic gases..... 0  
 Reacting with water..... 0  
 Active particles.....  
 Soluble solids as bulk chemical compounds.....

Hazardous substances / non hazardous pollutants: None expected.

Acrylamide.....  
 Benzene.....

**WASTE STREAM****9A51****FED Stainless Steel**

Chlorinated solvents.....  
 Formaldehyde.....  
 Organometallics.....  
 Phenol.....  
 Styrene.....  
 Tri-butyl phosphate.....  
 Other organophosphates.....  
 Vinyl chloride.....  
 Arsenic.....  
 Barium.....  
 Boron.....  
 Cadmium.....  
 Caesium.....  
 Selenium.....  
 Chromium.....  
 Molybdenum.....  
 Thallium.....  
 Tin.....  
 Vanadium.....  
 Mercury compounds.....  
 Others.....  
 Electronic Electrical Equipment (EEE)  
     EEE Type 1.....  
     EEE Type 2.....  
     EEE Type 3.....  
     EEE Type 4.....  
     EEE Type 5.....  
 Complexing agents (%wt): Yes  
     EDTA.....  
     DPTA.....  
     NTA.....  
     Polycarboxylic acids.....  
     Other organic complexants.....  
     Total complexing agents..... TR

**PACKAGING AND CONDITIONING**

Conditioning method: This stream is to be co-packaged with 9A63, 9A64, 9A83, 9A84, 9A33, 9A34, 9A35, 9A41, 9A42, 9A43, 9A49, 9A50, 9A54, 9A55, 9A56, 9A74. Packages are assigned to 9A33/C, 9A34, 9A74.  
 Plant Name: -  
 Location: Berkeley Site  
 Plant startup date: -  
 Total capacity (m<sup>3</sup>/y incoming waste): -

<b>WASTE STREAM</b>	<b>9A51</b>	<b>FED Stainless Steel</b>
---------------------	-------------	----------------------------

Target start date for packaging this stream: -

Throughput for this stream (m<sup>3</sup>/y incoming waste): -

Other information: -

Likely container type:	Container	Waste packaged (%vol)	Waste loading (m <sup>3</sup> )	Payload (m <sup>3</sup> )	Number of packages

Likely container type comment: -

Range in container waste volume: -

Other information on containers: -

Likely conditioning matrix: Other information: -

Conditioned density (t/m<sup>3</sup>): -

Conditioned density comment: -

Other information on conditioning: -

Opportunities for alternative disposal routing:

Treatment	Stream volume (%)	Comment
-	-	-

**RADIOACTIVITY**

Source: Activation when the associated fuel elements were irradiated, of nuclides incorporated into the stainless steel. Contamination by fission products and actinides when the fuel elements were in the fuel pond.

Uncertainty: The values quoted are indicative of the activities that might be expected.

Definition of total alpha and total beta/gamma: Where totals are shown on the table of radionuclide activities they are the sums of the listed alpha or beta/gamma emitting radionuclides plus 'other alpha' or 'other beta/gamma'.

Measurement of radioactivities: Specific activity is a function of Station operating history. Values were derived from calculations of induced activity and estimates of likely contamination.

Other information: -

**WASTE STREAM**

**9A51**

**FED Stainless Steel**

Nuclide	Mean radioactivity, TBq/m <sup>3</sup>				Nuclide	Mean radioactivity, TBq/m <sup>3</sup>			
	Waste at 1.4.2019	Bands and Code	Future arisings	Bands and Code		Waste at 1.4.2019	Bands and Code	Future arisings	Bands and Code
H 3	1.53E-03	CC 2			Gd 153		8		
Be 10		8			Ho 163		8		
C 14	6.00E-01	CC 2			Ho 166m		8		
Na 22		8			Tm 170		8		
Al 26	3E-06	CC 2			Tm 171		8		
Cl 36	7E-07	CC 2			Lu 174		8		
Ar 39		8			Lu 176		8		
Ar 42		8			Hf 178n		8		
K 40		8			Hf 182		8		
Ca 41		8			Pt 193		8		
Mn 53		8			Tl 204		8		
Mn 54	2.39E-08	CC 2			Pb 205		8		
Fe 55	4.22E+00	CC 2			Pb 210		8		
Co 60	<2.06E+01	C 3			Bi 208		8		
Ni 59	2E+00	CC 2			Bi 210m		8		
Ni 63	1.84E+02	CC 2			Po 210		8		
Zn 65		8			Ra 223		8		
Se 79		8			Ra 225		8		
Kr 81		8			Ra 226		8		
Kr 85		8			Ra 228		8		
Rb 87		8			Ac 227		8		
Sr 90	5.26E-05	CC 2			Th 227		8		
Zr 93	4E-09	CC 2			Th 228		8		
Nb 91		8			Th 229		8		
Nb 92	1E-07	CC 2			Th 230		8		
Nb 93m	1.80E+00	CC 2			Th 232		8		
Nb 94	8.00E-03	CC 2			Th 234	<5E-08	C 3		
Mo 93	7.00E-03	CC 2			Pa 231		8		
Tc 97		8			Pa 233	<6.29E-09	C 3		
Tc 99	1E-03	CC 2			U 232		8		
Ru 106		8			U 233		8		
Pd 107		8			U 234	5.08E-08	CC 2		
Ag 108m	1.96E-02	CC 2			U 235	1E-09	CC 2		
Ag 110m		8			U 236	7.00E-09	CC 2		
Cd 109		8			U 238	5E-08	CC 2		
Cd 113m	3.85E-09	CC 2			Np 237	6.29E-09	CC 2		
Sn 119m		8			Pu 236		8		
Sn 121m		8			Pu 238	1.82E-05	CC 2		
Sn 123		8			Pu 239	2E-05	CC 2		
Sn 126		8			Pu 240	3.00E-05	CC 2		
Sb 125	4.34E-09	CC 2			Pu 241	1.13E-03	CC 2		
Sb 126		8			Pu 242	2E-08	CC 2		
Te 125m	1.09E-09	CC 2			Am 241	8.77E-05	CC 2		
Te 127m		8			Am 242m	1.88E-07	CC 2		
I 129		8			Am 243	5.00E-08	CC 2		
Cs 134	1.78E-09	CC 2			Cm 242	1.55E-07	CC 2		
Cs 135		8			Cm 243	4.55E-08	CC 2		
Cs 137	5.30E-05	CC 2			Cm 244	3.79E-07	CC 2		
Ba 133	2.27E-06	CC 2			Cm 245		8		
La 137		8			Cm 246		8		
La 138		8			Cm 248		8		
Ce 144		8			Cf 249		8		
Pm 145		8			Cf 250		8		
Pm 147	8.42E-08	CC 2			Cf 251		8		
Sm 147		8			Cf 252		8		
Sm 151	1.82E-07	CC 2			Other a				
Eu 152	1.62E-09	CC 2			Other b/g		CC 2		
Eu 154	1.91E-07	CC 2			<b>Total a</b>	<b>1.57E-04</b>	<b>CC 2</b>	<b>0</b>	
Eu 155	3.65E-08	CC 2			<b>Total b/g</b>	<b>2.13E+02</b>	<b>CC 2</b>	<b>0</b>	

**Bands (Upper and Lower)**

- A a factor of 1.5
- B a factor of 3
- C a factor of 10
- D a factor of 100
- E a factor of 1000

Note: Bands quantify uncertainty in mean radioactivity.

**Code**

- 1 Measured activity
- 2 Derived activity (best estimate)
- 3 Derived activity (upper limit)
- 4 Not present
- 5 Present but not significant
- 6 Likely to be present but not assessed
- 7 Present in significant quantities but not determined
- 8 Not expected to be present in significant quantity