SITE Dungeness A SITE OWNER **Nuclear Decommissioning Authority WASTE CUSTODIAN** Magnox Limited LLW **WASTE TYPE** Is the waste subject to No Scottish Policy: **WASTE VOLUMES** Reported At 1.4.2022..... Stocks: 16.4 m³ Total future arisings: $0 \, \text{m}^3$ Total waste volume: 16.4 m³ Comment on volumes: Uncertainty factors on Stock (upper): x 1.1 Arisings (upper) Х volumes: Stock (lower): Arisings (lower) x 0.9 Х **WASTE SOURCE** Activated metals exposed to the neutron flux of the reactors during the operational stage of the site. PHYSICAL CHARACTERISTICS General description: The metals are mainly made up from duct seal sections, steel plate, angle iron, mild steel beams, steel box section and steel sheeting. Physical components (%wt): Mild steel (97.55%), Aluminium (2.40%), zinc (0.05%). The waste does not contain sealed sources. Sealed sources: Bulk density (t/m3): 0.69 Comment on density: WCH mass divided by volume. **CHEMICAL COMPOSITION** General description and Mild steel (97.55%), Aluminium (2.40%), zinc (0.05%). components (%wt): Chemical state: Neutral Chemical form of radionuclides: Metals and alloys (%wt): % of total C14 (%wt) Type(s) / Grade(s) with proportions activity Stainless steel..... Other ferrous metals..... 97.6 **Duct seal** section/beams/brackets/plates. Iron..... Aluminium..... 2.4 Plates/brackets/beams. Beryllium..... Cobalt..... Copper..... Lead..... Magnox/Magnesium..... Nickel..... Titanium.....

Uranium.....

	Zinc	0.05	Clips/brackets.	
	Zircaloy/Zirconium			
	Other metals			
Organic	s (%wt):			
		(%wt)	Type(s) and comment	% of total C14
	Total cellulosics	0		activity
	Paper, cotton			
	Wood			
	Halogenated plastics			
	Total non-halogenated plastics	0		
	Condensation polymers			
	Others			
	Organic ion exchange materials			
	Total rubber	0		
	Halogenated rubber			
	Non-halogenated rubber			
	Hydrocarbons			
	Oil or grease			
	Fuel			
	Asphalt/Tarmac (cont.coal tar)			
	Asphalt/Tarmac (no coal tar)			
	Bitumen			
	Others			
	Other organics			
Other m	aterials (%wt):			
		(0()	- ()	0/ // 1044
		(%wt)	Type(s) and comment	% of total C14 activity
	Inorganic ion exchange materials			
	Inorganic sludges and flocs			
	Soil			
	Brick/Stone/Rubble			
	Cementitious material			
	Sand			
	Glass/Ceramics			
	Graphite			
	Desiccants/Catalysts			
	Asbestos	0		
	Non/low friable			
	Moderately friable			
	Highly friable			
	Free aqueous liquids			
	Free non-aqueous liquids			

	Powder/Ash		
Inorganic ai	nions (%wt): -		
		(%wt)	Type(s) and comment
	Fluoride		
	Chloride		
	lodide		
	Cyanide		
	Carbonate		
	Nitrate		
	Nitrite		
	Phosphate		
	Sulphate		
	Sulphide		
	interest for - ptance criteria:		
		(%wt)	Type(s) and comment
	Combustible metals		
	Low flash point liquids		
	Explosive materials		
	Phosphorus		
	Hydrides		
	Biological etc. materials		
	Biodegradable materials	0	
	Putrescible wastes		
	Non-putrescible wastes		
	Corrosive materials		
	Pyrophoric materials		
	Generating toxic gases		
	Reacting with water	Р	10m2 per shipment maximum.
	Higher activity particles		
	Soluble solids as bulk chemical compounds		
	substances / - ous pollutants:		
		(%wt)	Type(s) and comment
	Acrylamide		
	Benzene		
	Chlorinated solvents		
	Formaldehyde		
	Organometallics		
	Phenol		
	Styrene		

Tri-butyl phosphate	9			
Other organophosp	phates			
Vinyl chloride				
Arsenic				
Barium				
Boron	0)		
Boron (in Boral).				
Boron (non-Bora	ıl)			
Cadmium				
Caesium				
Selenium				
Chromium				
Molybdenum				
Thallium				
Tin				
Vanadium				
Mercury compound	ds			
Others				
Electronic Electric	al Equipment (EEE)			
EEE Type 1				
EEE Type 2				
EEE Type 3				
EEE Type 4				
EEE Type 5				
Complexing agents (%wt):				
	('	%wt)	Type(s) and comme	nt
EDTA		,	,	
DPTA				
NTA				
Polycarboxylic acid	ds			
Other organic com	plexants			
Total complexing a	gents			
	Yes. Large Metal Iten "durable" assumed Dis		/"substantial" thickne	ess items considered

TREATMENT, PACKAGING AND DISPOSAL

Planned on-site / off-site treatment(s):

Treatment	On-site / Off site	Stream volume %
Low force compaction Supercompaction (HFC) Incineration Solidification Decontamination Metal treatment Size reduction Decay storage Recyling / reuse Other / various None	Off-site	100.0

Comment on planned treatments:

Waste is expected to be sent for metal treatment.

Disposal Routes:

Disposal Route	Stream volume %	Disposal density t/m3
Expected to be consigned to the LLW Repository Expected to be consigned to a Landfill Facility Expected to be consigned to an On-Site Disposal Facility Expected to be consigned to an Incineration Facility Expected to be consigned to a Metal Treatment Facility Expected to be consigned as Out of Scope Expected to be recycled / reused Disposal route not known	100.0	0.69

Classification codes for waste expected to be consigned to a landfill facility:

Upcoming (2022/23-2024/25) Waste Routing (if expected to change from above):

Disposal Route	Stream volume %			
Disposal Noute	2022/23	2023/24	2024/25	
Expected to be consigned to the LLW Repository Expected to be consigned to a Landfill Facility Expected to be consigned to an On-Site Disposal Facility Expected to be consigned to an Incineration Facility Expected to be consigned to a Metal Treatment Facility Expected to be consigned as Out of Scope Expected to be recycled / reused Disposal route not known				

Opportunities for alternative disposal routing:

			Estimated		
Baseline Management Route	Opportunity Management Route	Stream volume (%)	Date that Opportunity will be realised	Opportunity Confidence	Comment

Waste Packaging for Disposal: (Not applicable to this waste stream)

Container	Stream volume %	Waste loading m ³	Number of packages
1/3 Height IP-1 ISO 2/3 Height IP-2 ISO 1/2 Height WAMAC IP-2 ISO 1/2 Height IP-2 Disposal/Re-usable ISO 2m box (no shielding)			. 0
4m box (no shielding) Other			

Other information: -

Waste Planned for Disposal at the LLW Repository: (Not applicable to this waste stream)

Container voidage: -

Waste Characterisation

Form (WCH):

-

Waste consigned for disposal to LLWR in year of generation:

Non-Containerised Waste for In-Vault Grouting: (Not applicable to this waste stream)

Stream volume (%):

Waste stream variation:

Bounding cuboidal volume:

Inaccessible voidage: -

Other information:

RADIOACTIVITY

Source: Data based on 1MXN-3DUA-0-WCH-0-4653 V3 decayed two years for RWI 2022. The

determination of the fingerprint ratios for 9C916 from 9C911 can be seen in the 9C916 fingerprint implementation report. The radionuclides that ratio to Co-60 are reported in the desktop study review of 9C911 and 9C912 (DUNA/SED/179); the 9C911 activation product percentages and ratio values to Co-60 have been taken directly from that report and then

normalised to create 9C916.

Uncertainty:

Definition of total alpha and total beta/gamma:

Where totals are shown on the table of radionuclide activities they are the sums of the listed alpha or beta/gamma emitting radionuclides plus 'other alpha' or 'other beta/gamma'.

Measurement of radioactivities:

Dungeness A used the on site lab to gain gamma spectrometry results in October 2019. This showed that Co-60 was present in all of the samples and that Cs-137 and Am-241

were not detected above the MDA.

Other information: -

	ı	Mean radioactivity, TBq/m³			Mean radioactivity, TBq/m³		
Nuclide	Waste at 1.4.2022	Bands and Code	Future Bands an arisings Code	d Nuclide	Waste at Bands and 1.4.2022 Code	Future Bands and arisings Code	
H 3	6.07E-06	CC 2	anomge code	Gd 153	8	anonings Gods	
Be 10	0.07 2 00	8		Ho 163	8		
C 14	1.9E-06	CC 2		Ho 166m	8		
Na 22		8		Tm 170	8		
Al 26		8		Tm 171	8		
CI 36	6.98E-06	CC 2		Lu 174	8		
Ar 39	0.002 00	8		Lu 176	8		
Ar 42		8		Hf 178n	8		
K 40		8		Hf 182	8		
Ca 41		8		Pt 193	8		
Mn 53		8		TI 204	8		
Mn 54		8		Pb 205	8		
Fe 55	3.14E-06	CC 2		Pb 210	8		
Co 60	1.87E-06	CC 1		Bi 208	8		
Ni 59		8		Bi 210m	8		
Ni 63	3.83E-06	CC 2		Po 210	8		
Zn 65		8		Ra 223	8		
Se 79		8		Ra 225	8		
Kr 81		8		Ra 226	8		
Kr 85		8		Ra 228	8		
Rb 87		8		Ac 227	8		
Sr 90		8		Th 227	8		
Zr 93		8		Th 228	8		
Nb 91		8		Th 229	8		
Nb 92		8		Th 230	8		
Nb 93m		8		Th 232	8		
Nb 94	1.13E-07	CC 2		Th 234	8		
Mo 93		8		Pa 231	8		
Tc 97		8		Pa 233	8		
Tc 99		8		U 232	8		
Ru 106		8		U 233	8		
Pd 107		8		U 234	8		
Ag 108m	1.52E-07	CC 2		U 235	8		
Ag 110m		8		U 236	8		
Cd 109		8		U 238	8		
Cd 113m		8		Np 237	8		
Sn 119m		8		Pu 236	8		
Sn 121m		8		Pu 238	8		
Sn 123		8		Pu 239	8		
Sn 126		8		Pu 240	8		
Sb 125	3.91E-09	CC 2		Pu 241	8		
Sb 126		8		Pu 242	8		
Te 125m		8		Am 241	8		
Te 127m		8		Am 242m	8		
I 129		8		Am 243	8		
Cs 134		8		Cm 242	8		
Cs 135		8		Cm 243	8		
Cs 137		8		Cm 244	8		
Ba 133	2.83E-08	CC 2		Cm 245	8		
La 137		8		Cm 246	8		
La 138		8		Cm 248	8		
Ce 144		8		Cf 249	8		
Pm 145		8		Cf 250	8		
Pm 147		8		Cf 251	8		
Sm 147		8		Cf 252	8		
Sm 151		8		Other a			
Eu 152	1.31E-07	CC 2		Other b/g			
Eu 154	7.43E-08	CC 2		Total a	0 8	0	
Eu 155	2.67E-08	CC 2		Total b/g	2.43E-05 CC 2	0	
	1	J		1	Ī	<u>i</u>	

Bands (Upper and Lower)

A a factor of 1.5 B a factor of 3 C a factor of 10 D a factor of 100 E a factor of 1000

Note: Bands quantify uncertainty in

mean radioactivity.

- 1 Measured activity
 2 Derived activity (best estimate)
 3 Derived activity (upper limit)
 4 Not present
 5 Present but not significant
 6 Likely to be present but not assessed
 7 Present in significant quantities but not determined
 8 Not expected to be present in significant quantity
- 8 Not expected to be present in significant quantity